



DESCRIPTION

Cervac Board LT8 is a rigid product made by blending Mineral Fibre & Fiberfrax® Ceramic Fibre. Boards are vacuum formed from fibre containing slurry with organic & inorganic binders and mineral fillers. These are manufactured over a wide range of grades, sizes & thicknesses.

These boards may be used as back-up insulation depending on application temperature.

GENERAL CHARACTERISTICS

Cervac Board LT8 has the following outstanding characteristics :

- High temperature stability
- Low thermal conductivity & heat storage - saves fuel
- Highly resistance to thermal shock
- Resistance to erosion
- Easy to cut with standard tools

TYPICAL APPLICATIONS

- Back-up insulation for castable & bricks

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.



Unifrax India Private Limited (Formerly Unifrax India Limited)

C-102, Business Square, Andheri-Kurla Road, Andheri (East), Mumbai-400 093

T: +91 (22) 2921 2200 / 201 | F: +91 (22) 2921 2249 | unifrax.mumbai@unifrax.com | www.unifrax.com



TYPICAL PRODUCT PARAMETERS

Cervac Board	LT8
Physical Properties	
Classification Temperature (°C)	800
Density (kg/m ³)	>280
Hardness Shore Scale (avg.)	35
Flexural Strength (kg/cm ²)	6
Compressive Strength (kg/cm ²)	10% Comp. 2
	25% Comp. 3

The above strengths are for thickness upto 25mm, for higher thickness the strength will be lower.

Thermal Conductivity (W/mK)	
Mean Temp.	
250° C	0.10
550° C	0.11

Thermal Conductivity figures are empirical values (average) based on experience.

Permanent Linear Shrinkage (%) 24 Hour Soak	
Temp.	
800° C	1

For specification add 0.5% to above shrinkage value.

Water Repellant boards are available in LT Grade.

Classification temperature refers to the maximum short term temperature limit. The maximum continuous use limit depends upon application conditions. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office.

AVAILABILITY

Thickness (mm)	Pieces per Carton
Size : 500 x 1000 & 600 x 900	
6	20
12	11
19	7
25	6
38	4
50	3
75	2

Other thicknesses / sizes may be available on request subject to minimum order requirement.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by: