

PRODUCT:	SHRINKKOMP 10
TYPE:	GENERAL PURPOSE PLASTIC GROUT
NATURE OF BOND:	HYDRAULIC
INSTALLATION:	POURING AND RODDING

GENERAL PROPERTIES

Maximum Grain Size, mm 6

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Water Required for Plastic Consistency, %	12 – 14	13	ASTM C 1107, ASTM C 1090 & ASTM C 1437
Compressive Strength, Kgs / cm²			BS EN 12390 – 1 to 4
3 Days	150 – 220	200	
7 Days	210 – 310	300	
28 Days	320 – 400	380	
Linear Expansion, %			ACE test procedure TP/030 and ASTM C 806
Free	0.2 – 0.5	0.25	
Restrained	0.1 – 0.25	0.13	
% Retained Above Maximum Size	0 – 5	0.8	ASTM C 92

Packaging: 25 kg bags

Delivery State: Dry

Storage Life: Best till 6 months from the date of production, if stored in proper condition.

Note:

(1) The data are current production averages. They can not be used as limits for specification.